We create chemistry

Certificate of Analysis

BASF Polyurethanes GmbH

Please note that the certificates of analysis are also conveniently available on your BASF online portal.

BASF ARGENTINA S.A.

Tucuman 1

1049 Ciudad Autonoma de Buenos Aires
CIUDAD DE BUENOS AIRES
Argentina

2023-08-03 Certificate No 3369

Marcel Koeper

+49-5443-12-2199

Inspection Certificate 3.1 according to EN 10204

Elastollan* C 85 A 10 000

25KG Plastic film bags
Purchase order/Customer material
4977031770
000000000050080949

Material	50080949	
Order	2020832187	000010
Delivery	2036196489	000010
Lot	DE23389009	
Lot/Qty	15110.000	KG
Total	15110.000	KG
Transport	TCLU4076419	

Parameter	Method	Unit	Value	Lower Limit	Upper Limit
Density	DIN EN ISO 1183-1A	g/cm³	1,184	1,180	1,200
Shore A hardness	DIN ISO 48-4		83	83	87
Tensile strength	DIN 53504-S2	MPa	46	35	
Elongation break	DIN 53504-S2	% w/w	630	500	
Tear strength	DIN ISO 34-1 Bb	N/mm	65	60	
Abrasion loss	DIN EN 4649 A	mm3	43		45

MFR: Melt Flow Rate, according to this test-method.
Test platens: injection moulded from dry granulate with less than 0,05% water content.
Test platens tempered 20 hours at 100°C, then cooled to 23°C / 50 % RH before testing.
Test specimen cut from 2mm or 6mm test platens.

Statement of compliance with the order, with indication of results of specific inspection.
KöperPicker
Inspection representative

The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing of risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of ours can be derived therefrom.

This is a computer-generated document. No signature is required.